

测试报告

No. CANEC1605646404

日期: 2016年04月14日 第1页,共3页

东莞市立比精细化工有限公司

中国广东省东莞市厚街镇河田村远隆皮料市场A栋202

以下测试之样品是由申请者所提供及确认:油性色料(混合)

SGS工作编号: CP16-019379 - SZ

样品接收日期: 2016年04月07日

测试周期: 2016年04月07日 - 2016年04月14日

测试要求: 根据客户要求测试

测试方法: 请参见下一页

测试结果: 请参见下一页

结论: 按客户要求对样品进行测试,所提供样品的可溶性元素含量的测试结果不超过欧洲玩具安全标准EN 71-3:2013+A1:2014的限值。

通标标准技术服务有限公司广州分公司
授权签名

史丽兰

Violet, Shi 史丽兰

批准签署人

备注: 根据客户申请, SGS出具了此中文报告, 英文版本可根据客户要求提供. (The Chinese test report is issued according to the applicant's request. The English version is available from SGS if further needed)



SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch Testing Service Chemical Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

198 Kezhu Road, Science Park Guangzhou Economic & Technology Development District, Guangzhou, China 510663 t (86-20) 82155555 f (86-20) 82075113 www.sgs.com.cn
中国·广州·经济技术开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 f (86-20) 82075113 e sgs.china@sgs.com

测试报告

No. CANEC1605646404

日期: 2016年04月14日 第2页,共3页

测试结果:

测试样品描述:

样品编号	SGS样品ID	描述
SN1	CAN16-056464.002	黑色液体

备注:

- (1) 1 mg/kg = 1 ppm = 0.0001%
- (2) MDL = 方法检测限
- (3) ND = 未检出 (< MDL)
- (4) "-" = 未规定

EN 71-3:2013+A1:2014 - 可溶性元素含量(类别III:可刮取的玩具材料)

测试方法: 参考EN 71-3:2013+A1:2014, 采用 ICP-OES 进行分析。
六价铬用IC-UV/LC-ICP-MS/UV-VIS 进行分析。

测试项目	限值	单位	MDL	002
可溶性铝(Al)	70,000	mg/kg	50	ND
可溶性锑(Sb)	560	mg/kg	10	ND
可溶性砷(As)	47	mg/kg	10	ND
可溶性钡(Ba)	18,750	mg/kg	50	ND
可溶性硼(B)	15,000	mg/kg	50	ND
可溶性镉(Cd)	17	mg/kg	5	ND
可溶性三价铬(Cr (III))	460	mg/kg	5	ND
可溶性六价铬(Cr (VI))	0.2	mg/kg	0.18	ND
可溶性钴(Co)	130	mg/kg	10	ND
可溶性铜(Cu)	7,700	mg/kg	50	ND
可溶性铅(Pb)	160	mg/kg	10	ND
可溶性锰(Mn)	15,000	mg/kg	50	ND
可溶性汞(Hg)	94	mg/kg	10	ND
可溶性镍(Ni)	930	mg/kg	10	ND
可溶性有机锡	12	mg/kg	-	ND
可溶性硒(Se)	460	mg/kg	10	ND
可溶性锶(Sr)	56,000	mg/kg	50	ND
可溶性锡(Sn)	180,000	mg/kg	4.9	ND
可溶性锌(Zn)	46,000	mg/kg	50	ND

备注:



- 1 可溶性三价铬=可溶性总铬-可溶性六价铬
- 2.如果可溶性总锡的结果, 经过换算后不超过EN 71-3:2013+A1:2014 规定的可溶性有机锡的要求, 则不要
求做可溶性有机锡的确认性测试。

备注: 所示结果为烘干样品总重量中的含量。

样品照片:



此照片仅限于随SGS正本报告使用

*** 报告完 ***